

# Tred-MOR® 1562 SPECIFICATIONS

#### **SPECIFICATION DATA**

| Product Code:           | BV0171                                   |
|-------------------------|--|
| Product Name:           | Tred-MOR® 1562                           |
| Traffic Classification: | Extra-Heavy                              |
| Material Weight:        | 62 oz./sq. yd.                           |
| Density:                | 33 lbs./cu. ft.                          |
| Thickness:              | 0.156"                                   |
| Product Dimensions:     | 54" x 60' (30 sy.)                       |
| Mfg. Tolerances:        | Width: +/-1%<br>Thickness: +0.030/-0.015 |
| Approx. Shipping Wt.:   | 124 lbs. per roll                        |
| Color:                  | Black                                    |
| Material Content:       | Made with Synthetic Rubber               |
| Design Configuration:   | Flat/Flat                                |
| Backing Top:            | Spunbonded                               |
| Backing Bottom:         | Poly-Tek                                 |
| Antimicrobial:          | Guardian™                                |
| Moisture Resistant:     | 98%                                      |
| StainSTOP™:             | Yes                                      |
| Indoor Air Quality:     | CRI Green Label Plus-certified           |

#### **COMFORT AND DURABILITY**

| CLD PSI @ 25% Deflec. Min.:   | 7 (Method 601/12151)  |
|-------------------------------|-----------------------|
| CLD PSI @ 65% Deflec. Min.:   | 45 (Method 601/12151) |
| Breaking Strength PSI Length: | 45 (Min. ASTM-D2646)  |
| Breaking Strength PSI Width:  | 41 (Min. ASTM-D2646)  |
| Compression Set:              | 15%                   |

## FLAME CERTIFICATION

| Pill Test:             | Pass (DOC-FF 1-70) |
|------------------------|--------------------|
| Smoke chamber:         | Pass               |
| Flooring Radiant Panel | *                  |

<sup>\*</sup>Not applicable to separate carpet cushion. Carpet must be tested in composition with cushion.



## **ACOUSTICAL PERFORMANCE**

Impact Insulation Class (IIC): 71 (ASTM-492)
Sound Absorption (NRC): 0.30 (ASTM C423-81)

## THERMAL INSULATION

| R-Value: | 0.270 |
|----------|-------|
| K-Value: | 0.577 |

#### **OTHER**

| Meets Federal Spec.: | Class I (ZZ-00811B, Type I) |
|----------------------|-----------------------------|
| Electrostatic:       | 3.4 (AATCC-134)             |
| Toxicity:            | No more toxic than wood –   |
|                      | an accepted                 |
|                      | industry standard           |

## **PRODUCT FEATURES**

Tred-MOR is the nation's premium commercial carpet cushion. It is synonymous with Dubl-Stik®, and is the benchmark by which all others are measured. Tred-MOR can also be used in conventional stretch-in installation, and is available with QuikLIFT® backing.













